

PATENT ABSTRACTS OF JAPAN

(11)Publication number : 11-323195

(43)Date of publication of application : 26.11.1999

(51)Int.Cl.

C09D 5/00

B01D 53/86

B01J 35/02

C03C 17/23

C09D 1/00

(21)Application number : 11-068849

(71)Applicant : TOTO LTD

(22)Date of filing : 15.03.1999

(72)Inventor : SUGANO MITSUMASA
YAMAMOTO MASAHIRO
NORIMOTO KEIICHIRO
HAYAKAWA MAKOTO

(30)Priority

Priority number : 10 82880 Priority date : 13.03.1998 Priority country : JP

(54) PHOTOCATALYTIC COATING COMPOSITION

(57)Abstract:

PROBLEM TO BE SOLVED: To obtain a photocatalytic coating composition the foreign odor of which has been effectively masked without detriment to photocatalytic action and effects based thereon by mixing photocatalytic metal oxide particles with a perfume and a solvent.

SOLUTION: 90-20 wt.% photocatalytic metal oxide particles having a mean particle diameter of 1-100 nm, desirably, 1-50 nm are mixed with 10 wt.% or below, desirably, 0.0001-5 wt.% perfume, 10-80 wt.% difficultly decomposable binder, a mixed solvent comprising a water-soluble solvent having a boiling point of 120°C or above, a water-soluble solvent having a boiling point of 120°C or below, and water, and, optionally, 0.0005-2 wt.%, desirably, 0.001-2 wt.% surfactant, and an acid such as nitric acid or propionic acid in such amounts that the total of the photocatalytic metal oxide particles and the difficultly decomposable binder is 0.01-5 wt.% to obtain a photocatalytic coating composition which can give a coating film with a surface which, when excited with light, develops hydrophilicity or improves in its hydrophilicity.

LEGAL STATUS

[Date of request for examination]

[Date of sending the examiner's decision of rejection]

[Kind of final disposal of application other than the examiner's decision of rejection or application converted registration]

[Date of final disposal for application]

[Patent number]